



Pentacene Based Organic Field Effect Transistor Using Different Gate Dielectric

Ayat J. Kadhima^{a*}, Estabraq T. Abdullah^b, Abdulhadi K. Judranc^c

^aLaser and Optoelectronic Engineering Dept., University of Technology-Iraq, Alsina'a Street, 10066 Baghdad, Iraq.

^{b,c}College of Science Department of Physics, University of Baghdad, Baghdad, Iraq.

*Corresponding author Email: jkadhim950@gmail.com

HIGHLIGHTS

- Modeling of Organic field effect transistors were conceded.
- Focusing on the effect of dielectric materials on the OFET performance.
- Comparison between two different dielectric materials (PVP, ZrO₂) was considering.
- I-V characteristics were analyzed and studied.

ARTICLE INFO

Handling editor: Jawad K. Oleiwi

Keywords:

Dielectric materials
Organic field effect transistors
PVP
ZrO₂

ABSTRACT

This paper presents the electrical behavior of the top contact/ bottom gate of an organic field-effect transistor (OFET) utilizing Pentacene as a semiconductor layer with two distinctive gate dielectric materials Polyvinylpyrrolidone (PVP) and Zirconium oxide (ZrO₂) were chosen. The influence of the monolayer and bilayer gates insulator on OFET performance was investigated. MATLAB software was used to simulate and determine the electrical characteristics of a device. The output and transfer characteristics were studied for ZrO₂, PVP and ZrO₂/PVP as an organic gate insulator layer. Both characteristics show a high drain current at the gate dielectric ZrO₂/PVP equal to -0.0031A and -0.0015A for output and transfer characteristics respectively, this can be attributed to an increase in the dielectric capacitance. Trans conductance characteristics also studied the gate dielectric materials and show the ZrO₂/PVP gate dielectric having a higher value from the monolayer, indicating the effect of dielectric capacitance.

1. Introduction

Small molecular organic semiconductors have a great interest because of their good facilities, lightweight, and easy fabrication under the ambient condition at low cost [1]. The importance of organic semiconductors appears in devices such as transistors[2], solar cells [3], sensors [4], light-emitting diode [5]. Although, these materials typically exhibit low charge carrier mobility, poor environmental stability and a short operational lifetime comparing with inorganic counterparts [6]. Among these small semiconductors, Pentacene is a promising material for a modern application, it is an organic semiconductor molecule (C₂₂H₁₄) with high mobility and carrier and the most promising p-type materials to use in the fabrication of organic field-effect transistor (OFET) devices, typically its charge carrier mobility's ranging between 0.1 – 0.7 cm²/V.s. [7]. The gate dielectric materials and the interface between the gate dielectric materials and the active region are very effective in OFET performance. The organic-inorganic dielectric materials will play a significant role because of their features including low leakage current, decreases in threshold voltage and power dispersion with good thermal stability [8] [9]. Polymer dielectrics show several advantages against inorganic dielectric materials including transparent transistors and flexible display. One of the most interesting polymers is poly vinyl pyro linen (PVP), it is transparent, cross-linkable flexibility which has a great dielectric properties and a high transporter versatility of 3–5 cm²V¹s¹[10]. Numerous inorganic metal oxides of high-k concentrated to date incorporate HfO₂ [11], TiO₂ [12], Zirconium oxide (ZrO₂) [13]. This work aims to enhance the performance of Pentacene-based OFET depending on two different gate dielectric materials (ZrO₂and PVP) by using it as monolayer and bilayer.

2. Device Structure

Pentacene-based OFET with bottom-gate/top contact with 50nm thickness; the parameters used in this work are listed in Table 1. The schematic structure of the Pentacene-based OFETs has appeared in Figure 1.




Figure 1: Schematic of OFET

Table 1: Physical parameter for simulation structure

Parameter	Value
Channel length, L	1 μm
Thickness, t	100 nm
Channel width, W	2.1 μm
Dielectric constant for PVP, k	4.5
Dielectric constant for ZrO ₂ , k	23
Mobility, μ	5 Cm ² /V.S
Threshold voltage, V _{th}	360

3. Simulation

A typical model of field-effect transistors gives I_d in the direct regime [14].

$$I_d = \frac{WC_i}{L} \mu \times \left[(V_g - V_T) \times V_d - \frac{V_d^2}{2} \right] \tag{1}$$

With $V_d < V_g - V_T$

$$I_d = \frac{WC_i}{2L} \mu_{sat} \times (V_g - V_T)^2 \tag{2}$$

While the trans conductance of indirect and the immersion locale of the OFET is given by [15]

The Linear region
$$g_m = \frac{\partial I_d}{\partial V_g} = \mu C_i \frac{W}{L} V_d \tag{3}$$

The saturation region
$$g_m = \frac{\partial I_D}{\partial V_g} = \mu C_i \frac{W}{L} (V_g - V_T) \tag{4}$$

Where W and L are the channel width and length, individually. C_i the geometric capacitance of the dielectric layer, V_g is the voltage applied to the entryway contact, V_d is the voltage applied to the channel contact, and μ is the mobility. MATLAB recreation was utilized to extricate parameters, for example, portability from the electrical portrayal of Pentacene-based OFETs.

4. Results and Discussion

4.1 Output Characteristics

Figures 2 and 3 show OFET-based Pentacene for PVP and ZrO₂ as natural protector layers individually. It shows a regular yield bend of a field-effect transistor (FET) which demonstrates that solitary gaps are gathered at the semiconductor-dielectric interface and flow stream from the source to the channel through the channel area when negative entryway voltages are applied. In this way, the OFET is working in the p-direct activity in aggregation mode with expanding negative channel current.




Figure 2: Output Characteristics of gate insulator PVP




Figure 3: Output Characteristics of gate insulator ZrO2

The drain current increases with increasing the negative drain voltage till arises saturation region and this is because of the channel pinch-off. It can be the observed improvement of the drain current by using ZrO₂ insulator against PVP insulator such behavior can be attributed to the differences in dielectric constant for the two materials which leads to an increase in the effective capacitance C_i, which is defined as C_i, which is defined as [16]:

$$C_i = k \cdot \epsilon / t \tag{5}$$

Which the carriers charge density increasing too

$$Q = C_i (V_g - V_T) \tag{6}$$

Figure 4, shows more increase in the I_d for ZrO₂/PVP comparing with PVP and ZrO₂, because of the increase of the total dielectric capacitance C_{total}, which is given by Eq. (7):

$$C_{total} = C_{PVP} + C_{ZrO_2} \tag{7}$$

The highest current that can be obtained for ZrO₂/PVP of OFETs is I_d = -0.0031A at V_g = -40V. These high values of the drain current can be associated with the high capacitance of the ZrO₂/PVP layer.




Figure 1: Output Characteristics of gate insulator PVP/ZrO₂

4.2 Transfer Characteristics

Figure 5 shows the ordinary exchange qualities of OFET dependent on PVP, ZrO₂ and ZrO₂/PVP dielectric with V_g clearing from 0V to - 50V and V_d = -50V and thickness =100nm. Obviously, as the channel inclination expanded the channel field brings down the source to channel hindrance which builds the charge bearer Q, towards the start of the channel; they will cross the boundary, which in the end will prompt an increment of the channel current. The best estimations of the channel flow are gotten for dielectric material (ZrO₂/PVP) contrasting and PVP and ZrO₂. The most noteworthy estimation of the channel flow for the ZrO₂/PVP dielectric of OFETs was acquired right now 0.0015A at V_g = -40V. A diminishing in the channel current for all gate voltages contrasting and the most elevated estimation of the channel current at V_g = -50V, is identified with the edge voltage move as it were.

4.3 Trans conductance Characteristics

Figure 6 represents Trans conductance as a function of gate voltage for Pentacene OFET. At $V_g = 0V$ for gate insulator ZrO_2 , PVP and ZrO_2/PVP high Trans conductance is estimated to equal $gm = -0.5517 \times 10^{-4} A/V$, $-0.9931 \times 10^{-5} A/V$, and $-0.6511 \times 10^{-4} A/V$ respectively. It can be observed an improvement of the Trans conductance by using ZrO_2 insulator against PVP insulator, while the best values of the Trans conductance were obtained for dielectric material (ZrO_2/PVP) comparing with PVP and ZrO_2 . These results show an improvement of the trans conductance by using ZrO_2 insulator against PVP insulator, while the best values of the trans conductance are obtained for dielectric material (ZrO_2/PVP) comparing with PVP and ZrO_2 , and that is because the increase in the capacitance will induce more charge carriers by the same gate voltage, this behavior is in agreement with Demur et al. [17].




Figure 2: Transfer characteristics of gate insulator ZrO_2/PVP




Figure 3: Trans conductance of gate insulators PVP, ZrO_2 and ZrO_2/PVP

5. CONCLUSIONS

Top contact/ bottom gate Pentacene-based OFETs having a monolayer and bilayer of PVP and ZrO_2 as gate dielectric was studied. The electrical characteristics were calculated by using the MATLAB program in order to study the effect of gate dielectric on the device performance. The results show the best performance was bilayer ZrO_2/PVP than the monolayer PVP and ZrO_2 for I-V characteristics and trans conductance.

Author contribution

All authors contributed equally to this work.

Funding

This research received no specific grant from any funding agency in the public, commercial, or not-for-profit sectors.

Data availability statement

The data that support the findings of this study are available on request from the corresponding author.

Conflicts of interest

The authors declare that there is no conflict of interest.

References

- [1] J. L. Brédas, J. P. Calbert, D. A. Da Silva Filho, and J. Cornil, Organic semiconductors: A theoretical characterization of the basic parameters governing charge transport, Proc. Natl. Acad. Sci. U. S. A., 99, (2002), 5804–5809, doi: 10.1073/pnas.092143399.
- [2] Y. Yamashita, Organic semiconductors for organic field-effect transistors, in science and technology of advanced materials, 10, (2009), 1–9, doi: 10.1088/1468-6996/10/2/024313.
- [3] J. K. A. Kokil and K. Yang, Techniques for characterization of charge carrier mobility in organic semiconductors, J. Polym. Sci. PART B Polym. Phys., 50, (2012), 1130–1144, doi: 10.1002/polb.23103.
- [4] M. A. Najeeb, Z. Ahmad, and R. A. Shakoor, Organic thin-film capacitive and resistive humidity sensors: A Focus Review, Adv. Mater. Interfaces, 1800969, (2018), 1–19, doi: 10.1002/admi.201800969.

- [5] B. K. Periyasamy, S. K. Nayak, S. A. Kumar & J. S. Shankar, Device engineering aspects of organic light-emitting diodes (OLEDs), *Polym. Technol. Mater.*, 58, (2019), 1597–1624, doi: 10.1080/25740881.2018.1563133.
- [6] N. Karl, Charge carrier transport in organic semiconductors, *Synth. Met.*, 134, (2003), 649–657.
- [7] M. T. Hussein, E. K. Hassan, and E. T. And Abdullah, Study the high performance of organic semiconductor CuPc field effect transistor, (2015). [Online]. Available: <http://inpressco.com/category/ijcet>.
- [8] S. P. Haridas, S. Sreeshan, S. P. Jacob, S. Khan, and C. R. Azariah, Fabrication and characterization of flexible metal-insulator-semiconductor field effect transistor (MISFET) using organic ODS and inorganic ZrO₂ as dielectric stack materials, *Int. J. Trend Res. Dev.*, 4, (2017), 345–347.
- [9] L. Z. Y. Ran, T. F. H. YuFeng, C. ShaoBo, and H. Y. A. L. XiaoJun, Effects of gate dielectric thickness and semiconductor thickness on device performance of organic field-effect transistors based on pentacene, *Sci. CHINA Technol. Sci.*, 57, (2014), 1142–1146.
- [10] A. Assis, S. H. T. A, and P. Predeep, Organic field effect transistors – study of performance parameters for different dielectric layer thickness, in *AIP Conference Proceedings*, 1849, (2017), 020034.
- [11] S. Hall, O. Buiu, I. Mitrovic, Y. Lu, and W. Davey, Review and perspective of high-k dielectrics on silicon, *J. Telecommun. Inf. Technol.*, (2007), 33–43.
- [12] K. C. Y. Lu, W. H. Lee, H. S. Lee, and Y. Jang, Low-voltage organic transistors with titanium oxide-polystyrene bilayer dielectrics, *Appl. Phys. Lett.*, 94, (2009), 1–3, doi: 10.1063/1.3097010.
- [13] B. H. Mohammed and E. T. Abdullah, Comparison between horizontal and vertical OFETs by using poly (3-Hexylthiophene) (P3HT) as an active semiconductor layer, *Iraqi J. Sci.*, 61, (2020), 1040–1050, doi: 10.24996/ijsc.2020.61.5.13.
- [14] B. G. Horowitz, Organic Field-Effect Transistors, *Adv. Mater.*, 10, (1998), 365–377.
- [15] B. Thokchom, F. Meghdadi, S. Gues, N. Marjanovic, G. Horowitz, P. Lang, S. Bauer and N. S. Sariciftci, High-performance ambipolar pentacene organic field-effect transistors on poly (vinyl alcohol) organic gate dielectric, *Advanced Materials*, (2005), 2315–2320, doi: 10.1002/adma.200501109.
- [16] B. H. Mohammed and E. T. Abdullah, Study the performance of pentacene based organic field effect transistor by using monolayer, bilayer and trilayer with different gate insulators, *Iraqi J. Phys.*, 18, (2020), 85–97, doi: 10.20723/ijp.18.44.85-97.
- [17] M. A. Demir, A. Atahan, S. Balci and M. S. I. Aslan, Organic/inorganic interfaced field-effect transistor properties with a novel organic semiconducting material, *Philos. Mag.*, 96, (2016), 274–285, doi: 10.1080/14786435.2015.1130277.